

Vulca-NO! SPORT


by dinoflex

SPORT

RETAIL ■ HOSPITALITY ■ COMMERCIAL ■ EDUCATION



RECYCLED
RUBBER
FLOORING

A low-angle, dark photograph of ice hockey players in a locker room. The players are wearing white jerseys, dark pants, and helmets. They are standing in a line, looking towards the camera. The lighting is dramatic, with strong highlights on the players' faces and equipment, and deep shadows in the background. A large, dark, circular inset in the foreground shows a close-up of a dark, textured surface, likely the flooring being advertised.

Inspire confidence in every area of your facility with quality flooring underfoot. Our non-vulcanized process creates tough, odorless mats without the use of harmful solvents or VOC's. Whatever comes through your door, whether it's skate blades, metal cleats, rolling loads, or rough equipment edges, Dinoflex has got you covered.

Good for athletes.
Great for floors.

With its high density, Vulca-NO! is built to handle the toughest applications to protect your athlete and your floor.

Features

- Great traction - wet or dry
- Heavy duty dense material
- Impact absorbing
- Sound reducing
- Non-vulcanized
- Easy to clean

Benefits

- Reduces risk of injuries from slips & falls
- Eliminates the need to replace frequently
- Reduces soreness, fatigue in muscles & joints
- Decreases vibration & noise
- Certified for indoor air quality with no odor
- Low maintenance costs

Best For


Arenas

CrossFit Gym

Dugouts

Fitness Centers

Ski Resorts



Tolerance of +/- 0.5mm

Square Edge

48" x 72" = 24ft²

(121.92cm x 182.88cm)

Interlocking

46.82" x 70.23" = 22.83ft²

(118.92cm x 178.38cm)


STANDARD THICKNESS

7mm (9/32")

12mm (1/2")

15mm (19/32")

19mm (25/32")





Testing Results

DESCRIPTION	TEST METHOD	RESULT
Breaking Load & Elongation	ASTM D412	Breaking load: 115.89 Lbs. Elongation: 137.02% Tensile: 479.9 lbs/sq. inch
Coefficient of Friction: James Machine	ASTM D2047	Leather Dry = 1.12, Wet = 1.05
Hardness	ASTM D2240	73 Shore A
Taber Abrasion	ASTM D4060	0.20 Grams (0.19%) loss
Flexibility	ASTM F137	Passes - 6mm Mandrel
Static Load Limit	ASTM F970	0.005 Inch @ 250 psi
Deformation	ASTM F2157	0.6 mm
Dimensional Stability/Curling Properties	ASTM F2199	Length: -0.010" per 12 inches Width: -0.019" per 12 inches
Force Reduction	ASTM F2569	11.3%, Class 1
Force Reduction	ASTM F2772	Force Reduction: 11.3% Class 1
Ball Rebound		Ball Rebound: 98.5% Passes
Surface Finish Effect		Surface Finish Effect: 104 BPV Passes
Vertical Deflection / Deformation		Vertical Deflection/Deformation: 0.6 mm Class B
Slip Resistance	BM-III British Pendulum Skid Friction Coefficient Tester	Average COF: Dry = 0.83, Wet = 0.38

Please Note: All measurements are subject to nominal variation.

Dinoflex
P.O. Box 3309
5590 46 Ave SE
Salmon Arm, BC, Canada
V1E 4S1

Toll Free: 1-877-713-1899
Direct: 250-832-7780
sales@dinoflex.com
dinoflex.com



5 year Limited Warranty

when installed in accordance with
Dinoflex's Installation Guidelines.

Date Issued: