

Features

- High traction
- Withstands temperature fluctuations
- Impact absorbing
- Grid backing & water permeable
- No-glue interlocking system
- Easy to maintain

Benefits

- Slip resistant even when wet
- Will not buckle or crack under extreme outdoor temperature changes
- Reduces fall consequences
- Pourus in nature, allows water to flow through and create channels for drainage
- Easy and quick installation
- Advanced maintenance program not required

Best For

Apartment Complexes

Decks

Garden and Green Spaces

Health Care

Landscapes

Office Buildings

Balconies

Restaurants

Roofton Patios

Schools

Walkways



Interlocking Tile

 $24'' \times 24'' = 4ft^2$

 $(61cm \times 61cm = 0.37m^2)$

STANDARD THICKNESS

1" (25.4mm)

1 3/4" (44mm)

2 1/2" (69.85mm)

Interlocking System

Dinoflex self-aligning interlocking system provides for a fast and accurate installation. Interlocking tubes are included with every order for a nominal cost.



Interlocking Pins



Interlocking Tubes



Interlocking Tile



Tile Back

Color Swatches





FOREST GREEN







RED




EPDM Variations













25% BLUE

25% GREEN

25% BEIGE

25% BROWN

25% RED

25% ORANGE














50% BLUE

50% GREEN

50% BEIGE

50% BROWN

50% RED

50% ORANGE













75% BLUE

75% GREEN

75% BEIGE

75% BROWN

75% RED

75% ORANGE

Contact your Sales Representative for more information.

Colors shown are reproduced as closely as possible to actual product. Contact Dinoflex for product sample.



Click here to design your own Recycled Rubber Tile.





Testing Results

DESCRIPTION	TEST METHOD	RESULT
Aging Weathering	ASTM C67	No change
Aging Weathering	ASTM D573	No change
		Machine (Length) Direction: 24 hours submerged in 0.1% detergent solution at 23°C: +0.059% 24 hours in deep freeze at -18°C: +0.218% 72 hours in drying oven at 70°C: +0.455%
Dimensional Stability	DIN EN 13746	Forty eight hours conditioning at 20°C and 65% relative humidity: +0.457% Cross Direction:
		24 hours submerged in 0.1% detergent solution at 23°C: -0.205% 24 hours in deep freeze at -18°C: -0.201% 72 hours in drying oven at 70°C: -0.226% Forty eight hours conditioning at 20°C and 65% relative humidity: -0.224%
Water Drainage		4 litres drained in 306.71 seconds (5.1 minutes)

Please Note: All measurements are subject to nominal variation.

Dinoflex P.O. Box 3309 5590 46 Ave SE Salmon Arm, BC, Canada V1E 4S1

Toll Free: 1-877-713-1899 Direct: 250-832-7780 sales@dinoflex.com dinoflex.com







5-year limited warranty

when installed in accordance with Dinoflex's Installation Guidelines.

Date Issued: April 2025