A person is shown from the waist down, wearing a blue long-sleeved shirt and dark pants. They are in the process of tying a black roller skate with white laces. The background is a dark, textured floor. The text 'Vulca-NO! SKATE by dinoflex' is overlaid on the image.


# Vulca-NO! SKATE

by dinoflex

INDOOR ARENA ■ OUTDOOR ARENA



RECYCLED  
RUBBER  
FLOORING

A photograph of ice skaters in a locker room, viewed from behind, walking away from the camera. The scene is dimly lit with blue and white tones. A large circular inset on the left side of the image shows a close-up of the dark, textured flooring material.

The ultimate solution for skate-resistant flooring. Vulca-NO! Skate is specifically designed for arena applications, combining unmatched durability with superior safety. Its non-vulcanized composition ensures a low-VOC, chemical-free surface while offering exceptional impact absorption.

Good for athletes.  
Great for floors.

Built to endure heavy foot traffic and frequent skate use, Vulca-NO! Skate provides a reliable, long-lasting flooring solution that keeps your facility both protected and environmentally conscious.

## Features

- Great traction - wet or dry
- Heavy duty dense material
- Impact absorbing
- Sound reducing
- Non-vulcanized
- Easy to clean

## Benefits

- Reduces risk of injuries from slips & falls
- Eliminates the need to replace frequently
- Reduces soreness, fatigue in muscles & joints
- Decreases vibration & noise
- Certified for indoor air quality with no odor
- Low maintenance costs

## Best For

Arena Corridors  
Locker Room

Penalty Box  
Player Box

Wet Locker Room Area




Tolerance of +/- 0.5mm

**\*Available only in black**

## Square Edge

48" x 72" = 24ft<sup>2</sup>

(121.92cm x 182.88cm)



## STANDARD THICKNESS

7mm (9/32"), 12mm (1/2"), 15mm (19/32"),  
19mm (25/32")



## Testing Results

DESCRIPTION	TEST METHOD	RESULT
Breaking Load & Elongation - 12mm	ASTM D412	Breaking load: 115.89 Lbs. Elongation: 137.02% Tensile: 479.9 lbs/sq. inch
Coefficient of Friction: James Machine	ASTM D2047	Dry = 1.12, Wet = 1.05
Taber Abrasion	ASTM D4060	0.20 Grams (0.19%) loss
Flexibility	ASTM F137	Passes - 6mm Mandrel
Static Load Limit	ASTM F970	0.005 Inch @ 250 psi
Dimensional Stability/Curling Properties	ASTM F2199	Length: -0.010" per 12 inches Width: -0.019" per 12 inches
Force Reduction	ASTM F2569	11.3%, Class 1
Force Reduction Ball Rebound Surface Finish Effect Vertical Deflection / Deformation	ASTM F2772	Force Reduction: 11.3% Class 1 Ball Rebound: 98.5% Passes Surface Finish Effect: 104 BPV Passes Vertical Deflection/Deformation: 0.6 mm Class B
Slip Resistance	BM-III British Pendulum Skid Friction Coefficient Tester	Average COF: Dry = 0.83, Wet = 0.38

Please Note: All measurements are subject to nominal variation.

Dinoflex  
P.O. Box 3309  
5590 46 Ave SE  
Salmon Arm, BC, Canada  
V1E 4S1

Toll Free: 1-877-713-1899  
Direct: 250-832-7780  
[sales@dinoflex.com](mailto:sales@dinoflex.com)  
[dinoflex.com](http://dinoflex.com)

**5-year limited warranty**  
when installed in accordance with  
Dinoflex's Installation Guidelines.

Date Issued: May 2025



CERTIFIED BY  
SCS Global Services